

Product-Information

Mipa 2K-MS-Clear coat C 210 is an acrylic clear coat of high build properties and with UV protection. It can be applied **without** adding thinner. Excellent gloss and stability of the paint is assured even by one coat application. Therefore an important economy of material and processing time is obtained. It is ready to use after the addition of the suitable amount of Mipa 2K-Härter MS 10 or Mipa 2K-Härter MS 25. Excellent durability against all environmental and climatic circumstances, yellowing resistant and durable gloss.

Consumption: 6 - 8 m² / l.

Colour shade	transparent			
Mixing ratio	2 : 1 by volume			
Hardener	Mipa 2K - Härter MS 10, MS 25 or MS 40			
Thinners	without thinner			
Spraying viscosity 20° C	18 - 20 s 4 mm DIN			
Application	spraying pressure	spraying nozzle	spraying operations	
Air / Flowjar - Spray gun	4 - 5 bar	1,4 mm	1 - 2	
Airless / Airmix				
Pot life	4 - 6 h			
Coat thickness / dry film	40 - 50 µm			
Curing time / Flash off time	5 - 10 min. between the spraying operations			
Dry	recoat time	dust dry	set to touch	full hardness
Object temp. 20° C		30 min.	12 h	24 h
Object temp. 60° C		5 min.	30 min.	2 h

Operation conditions: from + 10 °C and up to 75% relative air humidity.
contains aliphatic polyisocyanate

All products should be disposed of in relation to the regulations of the environmental health authorities. Protect your Environment!

This technical data sheet is supplied for informational purposes only! According to our information, all data and recommendations correspond to the state of art and are based on years of experience in manufacturing our products. They do not exempt the user from his obligation to verify professionally, on his own responsibility, the suitability of our products to the intended purpose under prevailing conditions. Safety data sheets and warnings on packaging must be observed. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.