










Intended use

Mipa Steinschlagschutz UBS is a durable corrosion protection for floor pans, entry sections and wheel houses. Excellent sound deadening properties, therefore this product is also suitable for car boots, bonnets and so on. Excellent adhesion, shock and scratch resistance, free from asbestos, fast drying, permanently elastic also in extreme temperature fluctuations, recoatable and after drying resistant to cold cleaner.

Spreading rate: 2,0 m²/l (for 500 µm DFT)

Processing instructions

	Colour black, light grey, white					
	Mixing ratio					
	Hardener		by weight (lacquer : hardener)	by volume (lacquer : hardener)		
	--	--	--	--		
	Hardener for complete paintwork			for partial paintwork		
	--			--		
	Pot life --					
	Thinner ready for use					
	Spray viscosity gravity spray gun			Airmix/Airless		
	--			--		
	Application mode					
	Application mode	Hardener	pressure (bar)	nozzle (mm)	spray passes	Thinner
	underbody spray gun/ UBS	--	4 - 6	5 - 10	2	--
	Flash-off time 5 - 8 min between coats					
	Dry coat thickness 500 µm					
	Drying time					
	object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
	20 °C	--	--	--	--	1 - 2 h

Note

- Storage:** at least 1 year in unopened original container
- VOC Regulation :** EU limit value for this product (category B/e): 840 g/l
This product contains max. 840 g/l of VOC.
- Processing conditions:** from +10 °C and up to 80 % relative humidity. Ensure adequate air ventilation.
- Processing instructions:** The floor pan must be cleaned thoroughly and must be dry, free from dust, grease, oil and rust. Old non-adherent underbody coating must be removed. Mask beforehand motor, exhaust pipes, stub axles, cardan shaft and brake system as they must not be sprayed!